

## SURFACE TYPE

## STAIN-PROOF, METACREME, INTENSIFIA

## DRY-TREAT 40SK

	sq ft/quart	sqm/quart	sq ft/quart	sqm/quart
Basalt - Porous (Chinese)	70	7	N/A	
Basalt - Dense (European)	120	12	N/A	
Bluestone (basalt)	100	10	N/A	
Bluestone (USA Boston Bluestone)	60	6	50	5
Brick	60	6	60 (not face brick)	6 (not face brick)
Poured Concrete Dense	70	7	N/A	
Poured Concrete Medium	70	7	60	6
Concrete Paver (dry pressed)	40	4	40	4
Concrete Paver (wet cast)	70	7	60	6
Granite Flamed	60	6	N/A	
Granite Honed	80	8	N/A	
Granite Polished	120	12	N/A	
Grout Lines	300 linear feet	90 linear metres	300 linear feet	90 linear metres
Limestone Honed - Dense	70	7	60	6
Limestone Honed - Porous	50	5	50	5
Limestone Polished	100	10	N/A	
Limestone around salt water	N/A		Dip seal	
Marble Honed	100	10	N/A	
Marble Polished	150	15	N/A	
Porcelain - Honed and Polished	150	15	N/A	
Quartzite	100	10	N/A	
Saltillo	50	5	50	5
Sandstone (Indian, hard)	70	7	60	6
Sandstone (soft)	40	4	40	4
Sandstone around salt water	N/A		Dip seal	
Slate - Dense black	120	12	N/A	
Slate	70	7	N/A	
Terracotta dense	70	7	N/A	
Terracotta porous	50	5	50	5
Terrazzo	100	10	N/A	
Travertine honed	70	7	60	6
Travertine polished	100	10	N/A	
Travertine around salt water	N/A		Dip seal	
Victorian Encaustic Tile - medium porosity	70	7	N/A	
Victorian Encaustic Tile - very porous	40	4	N/A	